

Nanotoxicity of Graphene Oxide

Akere, Taiwo Hassan; Zigiotta de Medeiros, Aline Maria; Martinez, Diego Stéfani T.; Ibrahim, Bashiru; Ali-Boucetta, Hanene; Valsami-Jones, Eugenia

DOI:

[10.1016/j.aquatox.2023.106552](https://doi.org/10.1016/j.aquatox.2023.106552)

License:

Creative Commons: Attribution-NonCommercial-NoDerivs (CC BY-NC-ND)

Document Version

Publisher's PDF, also known as Version of record

Citation for published version (Harvard):

Akere, TH, Zigiotta de Medeiros, AM, Martinez, DST, Ibrahim, B, Ali-Boucetta, H & Valsami-Jones, E 2023, 'Nanotoxicity of Graphene Oxide: – Gold Nanohybrid to Daphnia magna', *Aquatic Toxicology*, vol. 260, 106552. <https://doi.org/10.1016/j.aquatox.2023.106552>

[Link to publication on Research at Birmingham portal](#)

General rights

Unless a licence is specified above, all rights (including copyright and moral rights) in this document are retained by the authors and/or the copyright holders. The express permission of the copyright holder must be obtained for any use of this material other than for purposes permitted by law.

- Users may freely distribute the URL that is used to identify this publication.
- Users may download and/or print one copy of the publication from the University of Birmingham research portal for the purpose of private study or non-commercial research.
- User may use extracts from the document in line with the concept of 'fair dealing' under the Copyright, Designs and Patents Act 1988 (?)
- Users may not further distribute the material nor use it for the purposes of commercial gain.


Where a licence is displayed above, please note the terms and conditions of the licence govern your use of this document.

When citing, please reference the published version.

Take down policy

While the University of Birmingham exercises care and attention in making items available there are rare occasions when an item has been uploaded in error or has been deemed to be commercially or otherwise sensitive.

If you believe that this is the case for this document, please contact UBIRA@lists.bham.ac.uk providing details and we will remove access to the work immediately and investigate.



Nanotoxicity of Graphene Oxide – Gold Nanohybrid to *Daphnia magna*

Taiwo Hassan Akere^{a,b,*}, Aline Maria Zigiotta de Medeiros^{c,d}, Diego Stéfani T. Martinez^{c,d},
Bashiru Ibrahim^{a,b}, Hanene Ali-Boucetta^b, Eugenia Valsami-Jones^{a,*}

^a School of Geography, Earth and Environmental Sciences, College of Life and Environmental Sciences, University of Birmingham, Birmingham B15 2TT, United Kingdom

^b Nanomedicine, Drug Delivery & Nanotoxicology (NDDN) Lab, School of Pharmacy, College of Medical and Dental Sciences, University of Birmingham, Birmingham B15 2TT, United Kingdom

^c Brazilian Nanotechnology National Laboratory (LNNano), Brazilian Centre for Research in Energy and Materials (CNPEM), Campinas, 13083-100, SP, Brazil

^d Centre of Nuclear Energy in Agriculture (CENA), University of São Paulo (USP), Piracicaba 13416-000, SP, Brazil

ARTICLE INFO

Keywords:

Ecotoxicity
Nanoparticles
Nanosafety
Nanobiotechnology

ABSTRACT

The expanding use of hybrid nanomaterials in many applications necessitates evaluation of their environmental risks. This study investigates the acute toxicity and bioaccumulation of graphene oxide – gold (GO-Au) nanohybrid in neonates (<24 hrs old) of *Daphnia magna* after exposure to a wide range of concentrations (1–100 mg/L). No significant mortality or immobilisation was observed after the exposure period. Microscopic observation showed an uptake of the nanohybrid and internal damage in the gut of the exposed organisms. Bioaccumulation of the GO-Au nanohybrid also occurred in a concentration-dependant manner. Continuous evaluation of the environmental risks from exposure to this nanohybrid and other advanced materials is imperative to avert disruption to the ecosystem.

Graphene oxide – gold nanohybrids (GO-Au) are advanced materials that have enhanced functionalities and remarkable properties that make them useful for diverse applications (Amir et al., 2020; Santhosh et al., 2014). The nanohybrid, produced via the chemical reduction of chloroauric acid by sodium citrate, have been used in biosensing, cancer therapy and bioimaging (Neri et al., 2019; Al-Ani et al., 2017; Turche-niuk et al., 2015). However, their widespread usage also makes them a subject of concern for toxicologists due to their potential environmental release. As it is with the fate of many nanomaterials, it is unavoidable that these GO-Au nanohybrids, once commercialised, will be released to the aquatic ecosystem (Pretti et al., 2014). Potentially, this could setoff deleterious effects to biota at each level of the food chain (Guo et al., 2013). With the uncertainty around the toxicity of GO-Au nanohybrids, it is vital to understand whether or not they might induce any acute or chronic harmful effect on sensitive organisms such as *Daphnia magna*. In addition, since daphnia are known to bioaccumulate chemicals (Du et al., 2016; Zhu et al., 2010; Xiaohui et al., 2018), an evaluation of the bioaccumulation of GO-Au nanohybrid becomes necessary to gain insight into how the nanohybrid may spread through the food web. There is also a potential risk to human health through the consumption of contaminated seafoods such as clams and fish (Klaper and Lyman, 2011).

The nanotoxicity of GO-Au nanohybrid has not been investigated before. Hence, this research aims to evaluate the toxicity of GO-Au nanohybrid to neonates (< 24 hrs old) of *Daphnia magna* in borehole water. Specifically, this work focused on assessing the acute immobilization/mortality and bioaccumulation of the nanohybrid by daphnia neonates.

Acute toxicity testing was carried out according to the Organisation for Economic Cooperation and Development (OECD) acute immobilization test protocol (OECD, 2004). *Daphnia* neonates (<24 hr old) were exposed to a range of concentrations (1, 5, 10, 20, 50 and 100 mg/L) of GO-Au nanohybrid for 48 hrs in borehole water. Natural organic matter (NOM, final concentration: 20 mg/L) was used to stabilise the nanohybrid in the media. Record of mortality and immobilization was taken at 24 and 48 hrs. Protocol for the preparation of the test solutions is presented in supplementary information.

Bioaccumulation was evaluated in daphnia neonates exposed to different concentrations of GO-Au nanohybrid (1, 50 and 100 mg/L) for 7 days. The culture media was changed on day 3 and 5. On day 7, daphnia samples were collected and rinsed with ultrapure water. The organisms were split into 3 groups: the first group was processed for quantification of gold nanoparticles (AuNPs) using inductively coupled plasma mass spectrometry (ICP-MS), the second group was processed for

* Corresponding author.

E-mail addresses: txa880@bham.ac.uk (T.H. Akere), e.valsamijones@bham.ac.uk (E. Valsami-Jones).

<https://doi.org/10.1016/j.aquatox.2023.106552>

Received 9 February 2023; Received in revised form 18 April 2023; Accepted 3 May 2023

Available online 12 May 2023

0166-445X/© 2023 The Author(s). Published by Elsevier B.V. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).




Fig. 1. Light microscope images of daphnids after exposure to different concentrations of GO-Au nanohybrid. (A) control, (B) 1 mg/L treatment, (C) 50 mg/L treatment (D)100 mg/L treatment.

imaging using transmission electron microscopy (TEM), and the last group was imaged (whole organism) using a light microscope.

The daphnia neonates in all the exposure concentrations had 100% survival except 100 mg/L where 93% survival was recorded. The result indicates that the GO-Au nanohybrid did not induce any lethal ecotoxicological effect (mortality and immobilization) to daphnia neonates at the tested concentrations (1–100 mg/L) in borehole media. According to the United Nations' global harmonised system of classification and

labelling of chemicals (United Nations 2011), the GO-Au nanohybrid is not considered hazardous to the aquatic environment. A combination of factors could possibly explain the low toxic effect of GO-Au nanohybrid on the neonates. The organisms may have depurated the nanohybrid, as is common with daphnia (Guo et al., 2013; Lv et al., 2018). Also, biodegradation of the GO-Au nanohybrid may have occurred in the digestive tract of the exposed daphnids. Some organisms such as insects and microorganisms have been reported to biodegrade graphene oxide nanocomposites (Fan et al., 2017; Liu et al., 2022). In addition, the presence of NOM in the media could mitigate the toxicity of the GO-Au nanohybrid (Zhang et al., 2019).

Morphological observation of the daphnia after exposure to GO-Au nanohybrid was carried out using a light microscope to enhance our understanding of the uptake and transport of the nanohybrid within the organism. As can be observed in Fig. 1, the GO-Au nanohybrid is present in the gut of the exposed daphnids except in the control. Also, the nanohybrids in the gut of the daphnids in the 50 and 100 mg/L treatments are noticeably more concentrated than those of the 1 mg/L exposure. These visual observations conform with the result of the AuNPs quantification in exposed daphnids. In addition, exposure of daphnia to potentially toxic elements and nanomaterials have been reported to have effects on embryonic development and induce tail loss and carapace shedding (Djekoun et al., 2015; Giardini et al., 2015; Ellis et al., 2020). However, the images show that the daphnids in all the treatments in this study have not lost body parts, agreeing with the




Fig. 2. Quantification of AuNPs in digested *Daphnia magna* samples after exposure to different concentrations of GO-Au nanohybrid for 7 days. Results represent the mean \pm standard deviation of three individual replicates.




Fig. 3. Representative images of cross sections of daphnia neonates by transmission electron microscope (TEM) after exposure to GO-Au nano hybrid (A = control; B = 1 mg/L; C&D = 50 mg/L; E&F = 100 mg/L) KEY: microvilli (MV), lysosome (L), mitochondria (M), nucleus (N), peritrophic membrane (PTM), vacuole (V), apical membrane (AM), AuNPs (Au).

outcome of the acute toxicity test that the GO-Au nano hybrid did not cause any significant harm to daphnia at the tested concentrations.

Due to the difficulty in directly quantifying carbon nanomaterials in biological systems (abundant background carbon, absence of reliable quantification method etc.) (Yang et al., 2013; Xin and Wan, 2019; Wang et al., 2013), the concentration of AuNPs in the nano hybrid was used in this study as a chemical label for GO-Au nano hybrid. It has been previously shown that AuNPs were homogeneously distributed on the GO-Au nano hybrid (Akere et al., 2023). Therefore, quantifying the amount of AuNPs in the exposed daphnids can be used to estimate the concentration of the GO-Au nano hybrid. The mean concentrations of AuNPs measured in 100 μ L of the digested daphnids ($n = 10$) exposed to 1, 50 and 100 mg/L of the nano hybrid were 0.0671 ± 0.002 , 0.2103 ± 0.008 and 0.2526 ± 0.006 mg/L respectively (Fig. 2). This result confirms the bioaccumulation of the GO-Au nano hybrid by daphnia neonates, posing potential threat to the health and safety of the organisms above daphnia in the food chain. Besides induction of oxidative stress and immobilisation, bioaccumulation of toxic substances can cause adverse effects on reproduction and development in aquatic organisms

(Fan et al., 2012; Cano et al., 2017).

To further evaluate the toxicity of GO-Au nano hybrid and its impacts on the organism's gut and internal organelles, TEM cross sectional images were taken and observed (Fig. 3). Common gut structures such as mitochondria (M) and lysosome (L) can be found in the control treatment (Fig. 3A). As expected, there were no traces of the GO-Au nano hybrid (as AuNPs) in the gut in the control treatment. However, AuNPs can be seen in the cross sections of all the remaining treatment samples (Fig. 3, B – F), confirming the uptake of the GO-Au nano hybrid by daphnia. This uptake is crucial and significant for bio-nano interaction which precedes the production of biological responses. In addition, internalization of the GO-Au nano hybrid may have led to over-generation of reactive oxygen species (ROS) which causes oxidative damage (Kwon et al., 2014). This sublethal effect could be responsible for the irregular shape and arrangement of organelles within the cells. An interaction of the GO-Au nano hybrid with the cells and formation of sizeable vacuole structures and lipid like cytoplasmic inclusions can be observed (Fig. 3C & F). GO-AuNPs can be seen within the cellular matrix (Fig. 3E), indicating that there may have been damages to the

peritrophic membrane. However, it is possible that a systemic effect may be produced on the whole organism following long duration exposures.

In conclusion, while neonates of *Daphnia magna* bioaccumulate GO-Au nanohybrid, significant acute toxic effects were not induced. This work represents a significant step in our understanding of the environmental risks associated with GO-Au nanohybrid. With the expanding use of GO-Au nanohybrid in various applications, there is a need for continuous evaluation of the nanosafety of the nanohybrid to the ecosystem and human health. Future research should focus on the chronic toxicity and sublethal effects (growth, reproduction, hormonal changes) of the GO-Au nanohybrid on daphnia.

Declaration of Competing Interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Data availability

No data was used for the research described in the article.

Acknowledgement

This research was funded by the Nigerian government through the Petroleum Technology Development Fund (PTDF) scholarship to T.H.A. and B.I. A.M.Z.d.M and D.S.T.M. thank CAPES and FAPESP foundations for scholarships, respectively, for visiting research at GEES/UoB. The authors are grateful to NANOTOX open-facility at LNNano/CNPem.

Supplementary materials

Supplementary material associated with this article can be found, in the online version, at doi:10.1016/j.aquatox.2023.106552.

References

- Akere, T.H., de Medeiros, A.M.Z., Martinez, D.S.T., Ibrahim, B., Ali-Boucetta, H., Valsami-Jones, E., 2023. Synthesis and characterisation of a graphene oxide-gold nanohybrid for use as test material. *Nanomaterials* 13 (1), 33. <https://doi.org/10.3390/nano13010033>.
- Al-Ani, L.A., AlSaadi, M.A., Kadir, F.A., Hashim, N.M., Julkapli, N.M., Yehye, W.A., 2017. Graphene-gold based nanocomposites applications in cancer diseases; efficient detection and therapeutic tools. *Eur. J. Med. Chem.* 139, 349–366. <https://doi.org/10.1016/j.ejmech.2017.07.036>.
- Amir, M.N.I., Halilu, A., Julkapli, N.M., Ma' amor, A., 2020. Gold-Graphene Oxide Nanohybrids: a Review on Their Chemical Catalysis. *J. Ind. Eng. Chem.* 83, 1–13. <https://doi.org/10.1016/j.jiec.2019.11.029>.
- Cano, A.M., Maul, J.D., Saed, M., Shah, S.A., Green, M.J., Cañas-Carrell, J.E., 2017. Bioaccumulation, stress, and swimming impairment in daphnia magna exposed to multiwalled carbon nanotubes, graphene, and graphene oxide. *Environ. Toxicol. Chem.* 36 (8), 2199–2204. <https://doi.org/10.1002/etc.3754>.
- Djekoun, M., Bensoltane, S., Bourechrouche, A., Bourechrouche, M., Berrebah, H., 2015. In vitro toxicity of cadmium on the development of parthenogenetic eggs of a freshwater cladoceran: daphnia magna. *J. Mater. Environ. Sci.* 6 (4), 957–962.
- Du, M., Zhang, H., Li, J., Yan, C., Zhang, X., Chang, X., 2016. Bioaccumulation, depuration, and transfer to offspring of ¹³C-labeled fullereneols by daphnia magna. *Environ. Sci. Technol.* 50 (19), 10421–10427. <https://doi.org/10.1021/acs.est.6b02596>.
- Ellis, L.J.A., Kissane, S., Hoffman, E., Brown, J.B., Valsami-Jones, E., Colbourne, J., 2020. Lynch, I. Multigenerational exposures of daphnia magna to pristine and aged silver nanoparticles: epigenetic changes and phenotypical ageing related effects. *Small* 16 (21). <https://doi.org/10.1002/sml.202000301>.
- Fan, J., Grande, C.D., Rodrigues, D.F., 2017. Biodegradation of graphene oxide-polymer nanocomposite films in wastewater. *Environ. Sci. Nano* 4 (9), 1808–1816. <https://doi.org/10.1039/C7EN00396J>.
- Fan, W., Shi, Z., Yang, X., Cui, M., Wang, X., Zhang, D., Liu, H., Guo, L., 2012. Bioaccumulation and biomarker responses of cubic and octahedral Cu₂O micro/nanocrystals in daphnia magna. *Water Res* 46 (18), 5981–5988. <https://doi.org/10.1016/j.watres.2012.08.019>.
- Giardini, J.L., Yan, N.D., Heyland, A., 2015. Consequences of calcium decline on the embryogenesis and life history of daphnia magna. *J. Exp. Biol.* 218 (13), 2005–2014. <https://doi.org/10.1242/jeb.123513>.
- Guo, X., Dong, S., Petersen, E.J., Gao, S., Huang, Q., Mao, L., 2013. Biological uptake and depuration of radio-labeled graphene by Daphnia Magna. *Environ. Sci. Technol.* 47 (21), 12524–12531. <https://doi.org/10.1021/es403230u>.
- Klaper, R.; Lyman, W. *Emerging contaminant threats and the great lakes: existing science, estimating relative risks and determining policies*; 2011.
- Kwon, D., Nho, H.W., Yoon, T.H., 2014. X-Ray and electron microscopy studies on the biodistribution and biomodification of iron oxide nanoparticles in daphnia magna. *Colloids Surfaces B Biointerfaces* 122, 384–389. <https://doi.org/10.1016/j.colsurfb.2014.07.016>.
- Liu, Z., Zhao, J., Lu, K., Wang, Z., Yin, L., Zheng, H., Wang, X., Mao, L., Xing, B., 2022. Biodegradation of graphene oxide by insects (tenebrio molitor larvae): role of the gut microbiome and enzymes. *Environ. Sci. Technol.* <https://doi.org/10.1021/ACS.EST.2C03342>.
- Lv, X., Yang, Y., Tao, Y., Jiang, Y., Chen, B., Zhu, X., Cai, Z., Li, B., 2018. A mechanism study on toxicity of graphene oxide to daphnia magna: direct link between bioaccumulation and oxidative stress. *Environ. Pollut.* 234, 953–959. <https://doi.org/10.1016/j.envpol.2017.12.034>.
- Neri, G., Fazio, E., Mineo, P.G., Scala, A., Piperno, A., 2019. SERS Sensing Properties of New Graphene/Gold Nanocomposite. *Nanomaterials* 9 (9), 1–13. <https://doi.org/10.3390/nano9091236>.
- OECD, 2004. Guideline 202: daphnia Sp., Acute Immobilisation Test. *OECD Guidel. Test. Chem.* 1–12. No. April.
- Pretti, C., Oliva, M., Pietro, R.Di, Monni, G., Cevasco, G., Chiellini, F., Pomelli, C., Chiappe, C., 2014. Ecotoxicity of Pristine Graphene to Marine Organisms. *Ecotoxicol. Environ. Saf.* 101 (1), 138–145. <https://doi.org/10.1016/j.ecoenv.2013.11.008>.
- Santhosh, C.; Saranya, M.; Ramachandran, R.; Felix, S.; Velmurugan, V.; Grace, A.N. G. Graphene/Gold Nanocomposites-Based Thin Films as an Enhanced Sensing Platform for Voltammetric Detection of Cr(VI) Ions. 2014, 2014.
- Turcheniuk, K., Boukherroub, R., Szunerits, S., 2015. Gold-Graphene Nanocomposites for Sensing and Biomedical Applications. *J. Mater. Chem. B* 3 (21), 4301–4324. <https://doi.org/10.1039/c5tb00511f>.
- United Nations, 2011. Globally Harmonized System of Classification and Labelling of Chemicals (GHS). <https://doi.org/10.1265/jjh.65.5>. Vol. 65.
- Wang, H., Yang, S.T., Cao, A., Liu, Y., 2013. Quantification of Carbon Nanomaterials in Vivo. *Acc. Chem. Res.* 46 (3), 750–760. <https://doi.org/10.1021/ar200335j>.
- Xiaohui, L., Tao, Y., Zhu, X., Jiang, Y., Li, B., Yang, Y., Chen, B., Cai, Z., 2018. A mechanism study on toxicity of graphene oxide to daphnia magna: direct link between bioaccumulation and oxidative stress. *Environ. Pollut.* 234, 953–959. <https://doi.org/10.1016/j.envpol.2017.12.034>.
- Xin, Y., Wan, B., 2019. A Label-Free Quantification Method for Measuring Graphene Oxide in Biological Samples. *Anal. Chim. Acta* 1079, 103–110. <https://doi.org/10.1016/j.aca.2019.06.036>.
- Yang, K., Li, Y., Tan, X., Peng, R., Liu, Z., 2013. Behavior and toxicity of graphene and its functionalized derivatives in biological systems. *Small* 9 (9–10), 1492–1503. <https://doi.org/10.1002/sml.201201417>.
- Zhang, Y., Meng, T., Shi, L., Guo, X., Si, X., Yang, R., Quan, X., 2019. The effects of humic acid on the toxicity of graphene oxide to scenedesmus obliquus and daphnia magna. *Sci. Total Environ.* 649, 163–171. <https://doi.org/10.1016/j.scitotenv.2018.08.280>.
- Zhu, X., Chang, Y., Chen, Y., 2010. Toxicity and bioaccumulation of tio₂ nanoparticle aggregates in daphnia magna. *Chemosphere* 78 (3), 209–215. <https://doi.org/10.1016/j.chemosphere.2009.11.013>.